

# NASA TECH BRIEF



NASA Tech Briefs are issued to summarize specific innovations derived from the U.S. space program, to encourage their commercial application. Copies are available to the public at 15 cents each from the Clearinghouse for Federal Scientific and Technical Information, Springfield, Virginia 22151.

## Study of High Temperature Bearing Materials

An experimental investigation has identified materials suitable for use in potassium lubricated turbo-generator journal bearing and shaft applications at temperatures from 400° to 1,600°F. Much of the information obtained during the program appeared useful to other high temperature bearing applications.

From a compiled list of 100 materials, 14 candidates were selected for detailed evaluation singly and in combination. The candidates represented five broad classes of materials: Nonrefractory metals and alloys, refractory metals and alloys, Fe-Ni-Co bonded carbides, refractory compounds (oxides, carbides, borides), and refractory metal bonded carbides.

Evaluation of the materials was based on the following experimental information:

- 1) Friction and wear behavior in high vacuum ( $10^{-9}$  torr; no lubrication).
- 2) Friction and wear behavior under boundary lubrication with liquid potassium.
- 3) Compatibility in potassium in Cb-1Zr.
- 4) Dimensional stability.
- 5) Strength.
- 6) Hardness.
- 7) Wettability by potassium.

Particular attention was given to the predicted chemical stability of the materials. Also, two separate service temperature regimes were established: above 1000°F and below 1000°F. The higher temperature simplifies system design. The lower simplifies bearing

materials selection.

The most appropriate materials for this service were: TiC + 10% Cb, commercial cobalt bonded carbides (e.g., carboloy 907 or equivalent material), a cold pressed and sintered alloy of tungsten and molybdenum. The first two groups of material were applicable above 1000°F and the third applicable below 1000°F.

### Notes:

1. Additional documentation is available from:  
Clearinghouse for Federal Scientific  
and Technical Information  
Springfield, Virginia 22151  
Price \$3.00  
Reference: TSP69-10252
2. Technical questions may be directed to:  
Technology Utilization Officer  
Lewis Research Center  
21000 Brookpark Road  
Cleveland, Ohio 44135  
Reference: B69-10252

### Patent status:

No patent action is contemplated by NASA.

Source: R. G. Frank of  
General Electric Company  
under contract to  
Lewis Research Center  
(LEW-10829)

Category 03